



Butyl Reclaim - Butyl(HT)

| Sr. | Properties | Unit of Measurement | Testing Method | Specification |
|-----|---------------------------------------|---------------------|---------------------------|---------------|
| 1 | Acetone Extract | % | ISO 1407 | 9 ± 3 |
| 2 | ASH Contain | % | ISO 247 | 5 ± 3 |
| 3 | Carbon Black | % | ISO 1408 | 28 ± 4 |
| 4 | Volatile Matter | % | ISO 248 | 1 Max |
| 5 | RHC by Difference | % | by Difference | 47 min. |
| 6 | Elongation at break | % | ISO 37, ISO/ DTS 16095 | 480 Min. |
| 7 | Hardness (Shore A) | - | ISO 7619 | 50 ± 4 |
| 8 | Mooney Viscosity ML (1+4) at 100°C | | ASTM D1646 | 35 ± 8 |
| 9 | Specific Gravity | Gm/CC | ISO 2781 | 1.14 Max |
| 10 | Tensile Strength | Kg/cm ² | ISO 37,ISO/ DTS 16095 | 90 Min |

