



Natural Tube Reclaim - NR

Sr.	Properties	Unit of Measurement	Testing Method	Specification
1	Acetone Extract	%	ISO 1407	11 ± 4
2	ASH Contain	%	ISO 247	25 ± 4
3	Carbon Black	%	ISO 1408	20 ± 7
4	Volatile Matter	%	ISO 248	1 Max
5	RHC by Difference	%	by Difference	47 min.
6	Elongation at break	%	ISO 37, ISO/ DTS 16095	230 Min.
7	Hardness (Shore A)	-	ISO 7619	60 ± 5
8	Mooney Viscosity ML (1+4) at 100°C		ASTM D1646	30 ± 15
9	Specific Gravity	Gm/CC	ISO 2781	1.25 ± 0.05
10	Tensile Strength	Kg/cm ²	ISO 37,ISO/ DTS 16095	35 Min

